



الواحة للدهانات
ALWAHA PAINTS

Since 1989 منذ



المعاجين
PASTES

معجون لاتكس

معجون مائي للأسطح الداخلية

LATEX PUTTY

Water Based Putty For interior Surface

الوصف

معجون بلاستيكي مصنع من أجود أنواع الراتنجيات. يستعمل على جميع الأسطح الأسمنتية الداخلية ليعطي سطحا ناعما.

المميزات

- للاستخدام الداخلي
- سهل الاستخدام.
- قدرة فائقة على ملء ألمسام والشقوق
- ذو معدل فرد عالي.
- يستخدم لتنعيم وتسوية الحوائط والأسقف قبل استخدام الدهانات البلاستيكية واللاكيهات.
- بياض جيد وقوة التصاق وسهولة فى الصنفرة.
- صديق للبيئة وخالي من الرصاص .

تعليمات الاستخدام

(1) إعداد السطح:-

- يراعى نظافة السطح المراد دهانه وخلوه من الزيوت والأثرية.
- فى حالة تطبيق المنتج على أسطح مدهونة مسبقا يراعى نظافة السطح وإزالة طبقة الدهانات الغير متماسكة وخلو السطح من أى مواد غريبة لضمان قوة الالتصاق.
- يراعى معالجة الأسطح المسامية باستخدام السيلر قبل تطبيق المعجون.

(2) خطوات التطبيق :-

- يستخدم برايمر الواحة أو سيلر الواحة لغلق المسام قبل تطبيق المعجون.
- يتم تطبيق معجون لاتكس دون إضافات.
- يراعى صنفرة سطح المعجون قبل تطبيق الدهان المناسب.
- ينصح بعمل طبقة من برايمر الواحة أو سيلر الواحة فوق المعجون وقبل الدهان لزيادة معدل فرد الدهان.

أدوات التطبيق

سكينة معجون – بروة بلاستيك - مالح

معدل الفرد

2.5- 3.5 م²/كجم (ويتوقف ذلك على طبيعة السطح) .

Description

Plastic Putty based on the best types of high quality resins could be used on all interior cementitious surface, and gives a smoothing surface.

Features

- For interior use
- Easy To Use.
- High ability to fill pores and cracks
- High Covering.
- Used for smoothing and leveling walls, ceiling prior to use of emulsion or alkyd paints.
- Good Whiteness, good adherence and can be easily sanded
- Environment friendly, lead free.

Instructions for use

1)Surface preparation:-

- Surface must be clean, free from oil, grease, dirt, etc.
- Old painted surfaces should be cleaned first from all loose paint and other materials that can affect adhesion.
- Absorbent substrates should be moistened with alwaha sealer before putty.

2)Application steps:-

- Use sealer & primer alwaha for priming purposes.
- Latex putty to be applied without further additions.
- Substrate should be sanded.
- The use of a sealer alwaha after puttying and before painting is recommended in order to increase spreading rate of finish paint.

Application tools

Knife – Plastic Trowel - Hawk

Spreading Rate

2.5-3.5m²/kg (according to surface nature)